

**IN THE CLAIMS:**

1. (Currently Amended): A water-soluble or water-dispersible polyurethane comprising the reaction product of

A) at least one polyether polyol a1) having a average functionality of  $\geq 3$  and at least one urethane group-containing polyether polyol a2) having an average functionality of  $\geq 4$ ,

B) at least one  $C_6$ - $C_{22}$  monoalcohol,

C) at least one (cyclo)aliphatic and/or aromatic diisocyanate,

D) optionally at least one  $C_4$ - $C_{18}$  monoisocyanate, and

E) optionally at least one polyisocyanate having an average functionality of  $> 2$ ,

wherein component C) comprises isophorone diisocyanate and the starting NCO/OH equivalent ratio is between 0.5:1 to 1.2:1 and the polyurethane has a softening point of from  $10^{\circ}\text{C}$  to  $80^{\circ}\text{C}$ , and

wherein the production of the polyether alcohol mixture A) containing polyethers a1) and urethane group-containing polyethers a2) is carried out by the partial reaction of polyethers a1) with at least one organic isocyanate having a functionality of  $\geq 2$  and up to 50 mole % the polyethers a1) are reacted with isocyanates.

2. (Previously Presented): The polyurethane of Claim 1, wherein the polyether polyol a 1) has an average functionality of 3 or 4.

3. (Previously Presented): The polyurethane of Claim 1, wherein the polyether polyol a1) has an average functionality of 4 to 6.

4. (Previously Presented): The polyurethane of Claim 1, wherein the component B) comprises a  $C_8$ - $C_{18}$  monoalcohol.

5. (Previously Presented): The polyurethane of Claim 1, wherein component

Mo6799

- 2 -

C) comprises a (cyclo)aliphatic diisocyanate.

6. (Previously Presented): The polyurethane of Claim 1, wherein component D) comprises a C<sub>8</sub>-C<sub>14</sub> monoisocyanate.

7. (Cancelled)

8. (Previously Presented): The polyurethane of Claim 1, wherein the urethane group-containing polyether polyol a2) is produced by a partial reaction of polyether polyol a1) with a diisocyanate.

9. (Previously Presented): The polyurethane of Claim 8, wherein the urethane group-containing polyether polyol a2) is produced by a partial reaction of polyether polyol a1) with a polyisocyanate having an average functionality of  $\geq 2$ .

10. (Currently Amended): A process for the production of the water-soluble or water-dispersible polyurethane of Claim 1, comprising reacting

A) a mixture of at least one polyether polyol a 1) having an average functionality of  $\geq 3$  and at least 1 urethane group-containing polyether polyol a2) having an average functionality of  $\geq 4$ ,

B) at least one C<sub>6</sub>-C<sub>22</sub> monoalcohol, at least one (cyclo)aliphatic and/or aromatic diisocyanate,

C) optionally at least one C<sub>4</sub>-C<sub>18</sub> monoisocyanate, and

E) optionally at least one polyisocyanate having an average functionality of  $> 2$

at a starting NCO/OH equivalent ratio of 0.5:1 to 1.2:1, component C) comprises isophorone diisocyanate, and the polyurethane has a softening point of from 10°C to 80°C.

11. (Previously Presented): In a process for adjusting the flow properties of an

Mo6799

- 3 -

aqueous paint system, adhesive and another aqueous formulation, the improvement comprising adding the polyurethane of Claim 1 thereto.

12. (Previously Presented): An aqueous paint system, adhesive and another aqueous formulation comprising the polyurethane of Claim 1.

Mo6799

- 4 -